

Method for Making Float Glass Having Reduced Defect Density

Related Application

This application claims the benefits of United States Provisional Application
5 Serial No. 60/414,516 filed September 27, 2002, which application is herein
incorporated by reference in its entirety.

Field of the Invention

The present invention relates to methods and related compositions for
10 reducing the defect density of glass; especially methods that can be used in float
glass processes including an oxy-fuel furnace.

Background of the Invention

The production of glass by the float glass process is well known in the art.
15 Generally, the float glass process involves mixing and heating various components of
a glass composition to produce a glass melt, pouring the glass melt onto a bath of
molten tin, and drawing the glass melt along the bath of molten tin to form a
dimensionally stable continuous sheet of glass.

Various components are added to the glass composition to yield glass having
20 different properties such as color, solar absorbance, strength, etc. The end use of
the glass determines the specific components required in the glass composition. For
example, in one instance, blue glass may be required so certain components will be
used in the composition. In another instance, green glass having a specific UV
absorbance may be required so different additives will be used to make up the
25 composition.

A component present in the glass melt is water. At the stage of the float glass
process when the glass melt is poured into a tin bath, some of the water diffuses out
of the glass melt and dissociates into hydrogen and oxygen at the glass-tin interface.
The tin, which has a very low solubility for hydrogen, is basically saturated with
30 hydrogen from the bath atmosphere so very little extra hydrogen can be dissolved in
the tin. Consequently, hydrogen from the disassociation of water gets trapped at the
interface between the molten glass and tin and ultimately impinges on the bottom
surface of the glass appearing as open bottom bubble defects in the bottom surface
of a glass article. The open-bottom bubbles can be described as voids in the glass

which generally have an inverted-U shape cross-section. The presence of open bottom bubbles increases the overall defect density of the glass.

Customers set requirements for the defect density of glass for certain applications. The standards are very difficult to meet with conventional float glass processes due to the presence of open bottom bubbles.

The present invention provides a novel method for reducing the open-bottom bubble defect density of glass produced in a float glass process, especially an oxy-fuel fired furnace.

10 Summary of the Invention

In one embodiment, the present invention is a method for reducing the defect density of float glass comprising:

melting a glass composition comprising:

- from 65-75 wt.% of SiO_2 ;
- 15 from 10-20 wt.% of Na_2O ;
- from 5-15 wt.% of CaO ;
- from 0-5 wt.% of MgO ;
- from 0-5 wt.% of Al_2O_3 ;
- from 0-5 wt.% of K_2O ;
- 20 from 0-2 wt % of FeO ; and
- from 0-2 wt% Fe_2O_3 ,

wherein the glass composition has a total field strength index of greater than or equal to 1.23.

In another embodiment, the present invention is a glass composition comprising:

- from 65-75 wt.% of SiO_2 ;
- from 10-20 wt.% of Na_2O ;
- from 5-15 wt.% of CaO ;
- from 0-5 wt.% of MgO ;
- 30 from 0-5 wt.% of Al_2O_3 ;
- from 0-5 wt.% of K_2O ;
- from 0-2 wt% FeO ; and
- from 0-2 wt.% Fe_2O_3 ,

wherein the glass composition has a total field strength index of greater than or equal to 1.23.

Description of the Invention

5 Unless otherwise indicated, all numbers expressing dimensions, physical characteristics, quantities of ingredients, reaction conditions and so forth, used in the specification and claims are to be understood as being modified in all instances by the term "about". Accordingly, unless indicated to the contrary, the numerical values set forth in the following specification and claims can vary depending upon the
10 desired properties sought to be obtained by the present invention. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques. Moreover, all ranges disclosed herein are to be understood to
15 encompass any and all subranges subsumed therein. For example, a stated range of "1 to 10" should be considered to include any and all subranges between (and inclusive of) the minimum value of 1 and the maximum value of 10; that is, all subranges beginning with a minimum value of 1 or more and ending with a maximum value of 10 or less, e.g., 5.5 to 10 or 3.2 to 7.8.

20 The present invention is a method for reducing the defect density of glass produced via a float glass process which is well known in the art. The invention can be used in float glass processes including either an air-fuel furnace or an oxy-fuel furnace. In an oxy-fuel furnace, oxygen, not air, supports combustion. However, the invention is particularly well suited for float glass processes that include an oxy-fuel
25 furnace.

 The present invention comprises melting a glass composition comprising
 from 65-75 wt.% of SiO_2 ;
 from 10-20 wt.% of Na_2O ;
 from 5-15 wt.% of CaO ;
30 from 0-5 wt.% of MgO ;
 from 0-5 wt.% of Al_2O_3 ;
 from 0-5 wt.% of K_2O ,
 from 0-2 wt% of FeO ; and
 from 0-2 wt% of Fe_2O_3 .

wherein the total field strength must be greater than or equal to 1.23.

The weight percents are based on the final oxide weight of the composition. The total amount of iron present in glass can be expressed in terms of Fe_2O_3 . However, this does not mean that all of the iron is actually in the form of Fe_2O_3 .

- 5 Similarly, the amount of iron can be reported as FeO , but this does not mean that all of the iron is actually in the form of FeO .

Additives can be included in the glass composition to attain certain color and/or solar or other performance.

- 10 Additives which can be added to the glass composition to achieve glass having a specific color are well known to those of ordinary skill in the art. Such additives include, but are not limited to, iron oxides (FeO and Fe_2O_3), cobalt, chromium, nickel, selenium, cerium, and/or titanium.

- 15 Other additives can be added to the glass composition to achieve glass having certain solar and other performance. These additives are well known to those of ordinary skill in the art. Such components include, but are not limited to, iron oxides, cobalt, chromium, vanadium, titanium, cerium, or any other conventional such materials.

- 20 Iron oxides can be included in a glass composition for several reasons. Ferric oxide, Fe_2O_3 , is a good ultraviolet radiation absorber and can give glass a yellow color. Ferrous oxide, FeO , is a good infrared radiation absorber and can give glass a blue color. With a proper balance of Fe_2O_3 and FeO , a green glass can be made.

- 25 In order to reflect the relative amounts of ferrous and ferric iron in a glass composition, the term "redox" will be used. As used herein, redox means the amount of iron in the ferrous state (FeO) divided by the amount of total iron. The term "total iron" is expressed in terms of Fe_2O_3 .

In a non-limiting embodiment of the invention, the glass composition comprises about 0.005 to 1.5 weight percent of total iron based on the weight percent of the composition.

- 30 CoO is a weak infrared radiation absorber and can provide a blue color to the glass. In a non-limiting embodiment of the invention, the glass composition comprises 0.0 to 500.0 ppm CoO .

Cr_2O_3 can provide a green color to the glass and some ultraviolet radiation absorption. In a non-limiting embodiment of the invention, the glass composition comprises 0.0 to 0.1 weight percent Cr_2O_3 based on the weight of the composition.

Se can provide ultraviolet and infrared radiation absorption and a pink to brown color to the glass. Se can also be used to decrease redox. In a non-limiting embodiment of the invention, the glass composition comprises 0.0 to 100.0 parts per million ("ppm") of Se.

5 TiO₂ can be used to provide ultraviolet radiation absorption and a yellow color to the glass. In a non-limiting embodiment of the invention, the glass composition comprises 0.0 to 2.0 weight percent TiO₂ based on the weight of the composition.

10 Vanadium (V₂O₅), can provide a yellow-green color and ultraviolet and infrared radiation absorption at different valence states. In a non-limiting embodiment of the invention, the glass composition comprises 0.0 to 0.5 weight percent of vanadium based on the total weight of the composition.

15 In various non-limiting embodiments, the glass composition of the present invention can include nickel, zinc oxide, erbium oxide, tin oxide, copper, manganese, neodymium, and/or molybdenum. For example, the glass composition can comprise 0.0 to 0.1 weight percent of nickel based on the total weight of the composition. For example, the glass composition can comprise 0.0 to 1.0 weight percent of zinc oxide based on the total weight of the composition. For example, the glass composition can comprise 0.0 to 3.0 weight percent of erbium oxide based on the total weight of the composition. For example, the composition can also comprise 0.0 to 2.0 weight percent of tin oxide based on the total weight of the composition. For example, the composition can comprise 0.0 to 0.5 weight percent of copper based on the total weight of the composition. For example, the composition can comprise 0.0 to 0.5 weight percent of manganese based on the total weight of the composition. For example, the composition can comprise 0.0 to 2.0 weight percent of neodymium based on the total weight of the composition. For example, the composition can comprise 0.0 to 300 ppm of molybdenum based on the total weight of the composition.

20 The glass composition of the present invention can also include small amounts of other materials like melting and refining aids, trace materials, impurities, etc. which are well known to one of ordinary skill in the art.

25 The glass composition of the present invention must have a certain total field strength (also known as the cation field strength). The total field strength of the glass composition must be greater than or equal to 1.23 or greater than or equal to 1.300. The expression for an individual cation field strength is Z^2/r , charge squared

divided by the radius. The total field strength of the glass composition is calculated as follows: the molar fraction of only the certain oxides is calculated first. For purposes of the present application, only the following oxides are considered in the total field strength calculation: SiO₂, Na₂O, CaO, MgO, Al₂O₃, K₂O, Fe₂O₃, and FeO. The number of cations/molecule is then multiplied by the mole fraction and the field strength for each cation to obtain the contribution to the total field strength from each oxide. The total field strength is the sum of each oxide contribution.

The table below shows a base field strength calculation for a glass composition.

10

Oxide	Amount Wt%	Molar fraction	Cation Field Strength	No. of cations/molecule	Field Strength Contribution
SiO ₂	71.59	.7104	1.57	1	1.115
Na ₂ O	13.9	.1335	0.19	2	0.051
CaO	7.99	.0849	0.33	1	0.028
MgO	3.80	.0561	0.45	1	0.025
Al ₂ O ₃	1.49	.0087	0.84	2	0.015
K ₂ O	1.00	.0063	0.13	2	0.002
Fe ₂ O ₃	0.08	.0002	0.85	2	0.0003
FeO	0.04	.0003	0.43	1	0.0001
<u>Total Field Strength</u>					1.236

A very small change in the weight percent of the oxides used to calculate the total field strength present in a glass composition can drastically affect the total field strength of the composition. Therefore, a slight change in the composition with respect to certain oxides can cause the total field strength to fall outside of the required range for the present invention.

In a float glass process, the glass composition is poured into a tin bath after it is melted. The glass melt coming into the tin bath can contain water. The glass melt can have a water content equal to or greater than 0.035 weight percent based on the total weight percent of the composition. The water content can be measured in the lab using spectral analysis.

The glass melt is subjected to further processing as is well known in the art to produce flat glass sheets of various thicknesses. Non-limiting examples of suitable float glass processes are disclosed in US Patent No. 3,083,551, US Patent No. 3,961,930, and US Patent No. 4,091,156 which are all hereby incorporated by
5 reference.

According to the present invention, glass can be produced that has reduced defect density; particularly open-bottom bubbles defects.

Defects in glass can be measured using on-line and off-line methods. An Automatic Inspection System manufactured by Inspection Technologies Inc. can be
10 used to measure defects on-line. Defects can also be measured off-line by visual inspection. The measured defects include surface as well as internal defects. By reducing the number of open-bottom bubble defects, the invention reduces the overall defect density of glass. The defect density of glass is measured as number of defects per 100 square feet.

15 Glass produced according to the present invention can meet the various commercial standards for defect density. For example, car manufacturers set standards for defect density for automotive windshields. One automobile manufacturer requires an automotive windshield to have zero defects. Any piece of glass having a defect is discarded in the factory. In such a case, if the number of
20 defects in the glass exceeds 1 per 100 Sq. ft., the float process yield becomes too low for the operation to be profitable.

The present invention also encompasses a glass composition comprising:

from 65-75 wt.% of SiO_2 ;
from 10-20 wt.% of Na_2O ;
25 from 5-15 wt.% of CaO ;
from 0-5 wt.% of MgO ;
from 0-5 wt.% of Al_2O_3 ;
from 0-5 wt.% of K_2O ;
from 0-2 wt.% Fe_2O_3 , and
30 from 0-2 wt % FeO ,

wherein the glass composition has a total field strength index of greater than or equal to 1.23.

The weight percents are based on the final weight of the composition. The composition can also include all of the additional components which are discussed above.

The method and related glass composition of the present invention can be used to form numerous glass articles such as, but not limited to, glass ribbons, laminated articles such as automotive windshields, tempered glass articles, side lights, back lights, architectural glass products, etc.

In a non-limiting embodiment of the invention, the glass article can be used to form a laminated product as is well known in the art. At least one of the pieces of glass in the laminated product can be produced according to the present invention. The laminated product can be a windshield having less than 1 total defects per 100 square feet.

Example

The following non-limiting examples illustrate the present invention. Table 1 shows various glass compositions according to the present invention. The weight percents are based on the total weight of the composition.

Table 1. Glass Compositions

	Clear Glass #1	Clear Glass #2	Green Glass #1	Green Glass #2
Component	[wt%]	[wt%]	[wt%]	[wt%]
SiO₂	71.59	72.35	72.77	72.56
Na₂O	13.9	13.8	13.59	13.4
K₂O	1	0.71	0.067	0.078
CaO	7.99	7.86	9.58	9.62
MgO	3.8	3.88	3.1	3.02
Al₂O₃	1.49	1.11	0.19	0.25
Fe₂O₃	0.08	0.09	0.35	0.47
FeO	0.04	0.04	0.13	0.21
SO₃	0.088	0.117	0.146	0.119
SrO	0.007	0.005	0.006	0.006
ZrO₂	0.009	0.023	0.011	0.014
Cl	0.008	0.006	0	0
Cr₂O₃	0.0007	0.0009	0.0007	0.001

- 9 -

MnO2	0	0	0.0022	0.0026
Mo	0	0	0	0.0015
BaO	0	0	0.01	0.01
TiO2	0	0	0.045	0.225
CeO2	0	0	0	0
SnO2	0	0	0	0

Base Field

Strength	1.236	1.240	1.237	1.238
-----------------	-------	-------	-------	-------

The above examples are offered only to illustrate the present invention. The scope of the present invention is defined by the following claims.